

## **TEST REPORT**

No.: SHIN1605021525MR

Date: May 17, 2016

Page: 3 of 4

Test Item: Striker Impacted by a Falling Weight

Sample Description: White Plastic part

Test Method: ASTM D4226-11 Procedure A and client's requirement

Test Condition:

Pretreatment: -30°C, 24h Specimen thickness: 4.0mm

Geometry: H.25

Strike weight: 3.6kg

Test Result:

Sample	Test Result
1	Mean failure height: 114.3 mm
	Mean failure energy: 4.0 J

Note: Test specimens were cut from the sample.



of the law. Offices orderwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are ad for 30 days only.

tion: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, all: CN.Doccheck@gs.com

No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China 201319 t (86-21) 61196300 f (86-21) 68183122/68183920 www.sgsgroup.com.cn